

Chemical Resistance Guide

CHEMICAL ENVIRONMENT	TYPE 'VEFR-20'		TYPE 'IFR-25'	
	% CONCENTRATION	MAX. OPER. TEMP F/C	% CONCENTRATION	MAX. OPER. TEMP. F/C
Acetic Acid	50	180/82	50	125/52
Aluminum Hydroxide	100	180/82	100	160/71
Ammonium Chloride	All	210/99	All	170/77
Ammonium Hydroxide	28	100/38	28	N/R
Ammonium Bicarbonate	50	160/70	15	125/52
Ammonium Sulfate	ALL	210/99	ALL	170/77
Benzene	N/R	N/R	N/R	N/R
Benzoic Acid	SAT	210/99	SAT	150/66
Borax	SAT	210/99	SAT	170/77
Calcaum Carbonate	ALL	180/82	ALL	170/77
Calcium Nitrate	ALL	210/99	ALL	180/82
Carbon Tetrachloride	100	150/65	N/R	N/R
Chlorine, Dry Gas	-	210/99	-	140/60
Chlorine Water SAT	200/93	SAT	80/27	
Chromic Acid	10	150/65	5	70/21
Citric Acid	ALL	210/99	ALL	170/77
Copper Chloride	ALL	210/99	ALL	170/77
Copper Cyanide	ALL	210/99	ALL	170/77
Copper Nitrate	ALL	210/99	ALL	170/77
Ethanol	50	100/38	50	75/24
Ethylene Glycol 100	200/93	100	90/32	
Ferric Cholride	ALL	210/99	ALL	170/77
Ferrous Chloride	ALL	210/99	ALL	170/77
Formaldehyde	ALL	150/65	50	75/24
Gasoline	100	180/82	100	80/27
Glucose	100	210/99	100	170/77
Glycerine	100	210/99	100	150/66
Hydrobromic Acid	50	150/65	50	120/49
Hydrochloric Acid	37	150/65	37	75/24
Hydrogen Peroxide	30	150/65	5	100/38
Lactic Acid	ALL	210/99	ALL	170/77
Lithium Chloride	SAT	210/99	SAT	150/66
Magnesium Chloride	ALL	210/99	ALL	170/77
Magnesium Nitrate	ALL	210/99	ALL	140/60
Magnesium Sulfate	ALL	210/99	ALL	170/77
Mercuric Chloride	100	210/99	100	150/66
Mercurous Chloride	ALL	210/99	ALL	140/60
Nickel Chloride ALL	210/99	ALL	170/77	
Nickel Sulfate	ALL	210/99	ALL	170/77
Nitric Acid	20	120/49	20	70/21
Oxalic Acid	ALL	210/99	ALL	75/24
Perchloric Acid 30	100/38	N/R	N/R	
Phosphoric Acid	100	210/99	100	120/49
Potassium Chloride	ALL	210/99	ALL	170/77
Potassium Dichromate	ALL	210/99	ALL	170/77
Potassium Nitrate	ALL	210/99	ALL	170/77
Potassium Sulfate	ALL	210/99	ALL	170/77
Propylene Glycol	ALL	210/99	ALL	170/77
Sodium Acetate	ALL	210/99	ALL	160/71
Sodium Bisulfate	ALL	210/99	ALL	170/77
Sodium Bromide	ALL	210/99	ALL	170/77
Sodium Cyanide	ALL	210/99	ALL	170/77
Sodium Hydroxide	25	180/82	N/R	N/R
Sodium Nitrate ALL	210/99	ALL	170/77	
Sodium Sulfate ALL	210/99	ALL	170/77	
Stannic Chloride	ALL	210/99	ALL	160/71
Sulfuric Acid	75	100/38	25	75/24
Tartaric Acid	ALL	210/99	ALL	170/77
Vinegar	100	210/99	100	170/77
Water, Distilled 100	180/82	100	170/77	
Zinc Nitrate	ALL	210/99	ALL	170/77
Zinc Sulfate	ALL	210/99	ALL	170/77

ALL...ALL Concentrations SAT...Saturated Solution N/R...Not Recommended -...No Information Available

The corrosion resistance data listed above is for general information only. Resin manufacturers have provided test data which indicates that the specific resin can withstand the corrosion conditions listed above. Delta Composite Structures believes the data to be true and accurate but no guarantee is expressed or implied as to specific performance. Testing for specific environments is recommended. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material sold by Delta Composite Structures, LLC.